

TECHNICAL DATA SHEET 635

Page 1 of 2


Uniform Silica Microspheres

DESCRIPTION

Polysciences, Inc. offers uniform, non-porous silica (SiO₂) microspheres available in nominal diameters of ~150nm-5µm. These particles typically have size CVs of 10-15%.

Inorganic supports such as silica microspheres have become increasingly important for a variety of applications, including isolation of nucleic acids, cell separation, and immuno- and DNA-based assays. They offer the combined benefits of a broad platform and the unique properties of a silica substrate:

- Flexible silanization chemistries
- Unique refractive index and density
- Low autofluorescence
- Low nonspecific binding of many biomolecules
- Hydrophilicity
- Ease of handling



Scanning Electron Microscope image of our (4.14µm) silica microspheres.

CHARACTERISTICS

Composition:	SiO ₂ , nonporous
Surface Groups:	SiOH (non-functionalized); NH ₂ or COOH; streptavidin
Refractive Index:	~1.43-1.46 (589nm)
Density:	2.0 g/cm ³
Glass Transition Temp:	>>1000°C*

* Reported value for bulk silica.

NOTES

1. **Aggregation:** If observed, aggregation may be treated using sonication (bath sonicator, ~10 minutes; probe sonicator, ~1 minute).

2. **Washing:** Standard washing methodologies are recommended, i.e. centrifugation where practicable, and dialysis or filtration for microspheres <500nm. Please note that carboxyl (COOH) or amine (NH₂) surface groups are in equilibrium with those in the suspending solution. It is therefore expected that some amount of surface groups will be removed with each wash.
3. **Transitioning Microspheres into a Solvent and Drying:** Silica microspheres >0.5µm in diameter may be dried to a powder. To dehydrate the surface (removed adsorbed water), the microspheres should first be washed with an organic solvent, such as ethanol or THF. Researchers should then begin by transitioning the microspheres from an aqueous buffer to solutions of increasing solvent concentration, and then separating them from solution (via settling, centrifugation or filtration). The microspheres are then dried from a moist cake, either in the open air or in a drying oven (e.g. 24 hours at 70°C). The dry cake may be crushed to a powder with a mortar and pestle.
4. **Suspending Dry Microspheres:** Dry silica microspheres may be dispersed in aqueous buffers or solvents (e.g. ethanol, methanol, THF or DMSO). An appropriate amount of silica powder should be added to the fluid of interest (dilute suspensions are easier to handle), and rigorously vortexed. The vial or tube containing the silica suspension should then be placed in a sonic bath. (*Note:* Probe sonicators are typically ineffective for dispersing powders.) Bath sonicate for ~10 minutes, and confirm that the microspheres are dispersed by viewing a drop of suspension under a light microscope (400X magnification). Individual microspheres 1µm or larger may be discerned at this magnification, and clumps of smaller microspheres will be clearly visible. If clumps are visible, continue to bath sonicate for 10 minute cycles until the spheres are fully dispersed.
5. **Coating Microspheres:** To covalently couple biomolecules to silica microspheres, the spheres must first be derivatized. This typically involves the regeneration of hydroxyl groups through an acid incubation (2N nitric acid at room temperature for 1 hour with rotation) followed by immediate silanization, or drying and later silanization. Acid-washed or derivatized (silanized) spheres should be stored dry with a desiccant. See the References section for additional protocols.

Adsorption is a common strategy for the assembly of lipid bilayers and for the isolation of nucleic acids. Silica microspheres may be coated with proteins via adsorption; however, as desorption of protein from the hydrophilic bead surface is expected to occur over time, covalent coupling is a better coating strategy for applications that require long-term stability. See the Storage and Stability section below.

REFERENCES

- Cras, J.J., C.A. Rowe-Taitt, D.A. Nivens, F.S. Ligler.** 1999. Comparison of cleaning methods of glass in preparation for silanization. *Biosens Bioelectron*, 14(8-9):683-688.
- Falipou, S., J.M. Chovelon, C. Martelet, J. Margonari, D. Cathignol.** 1999. New use of cyanosilane coupling agent for direct binding of antibodies to silica supports. Physicochemical characterization of molecularly bioengineered layers. *Bioconjugate Chem*, 10(3):346-353.
- Iler, R.K.** 1979. *The chemistry of silica: solubility, polymerization, colloid and surface properties, and biochemistry*. New York: John Wiley & Sons.
- Kumar, A., O. Larsson, D. Parodi, Z. Liang.** 2000. Silanized nucleic acids: a general platform for DNA immobilization. *Nucleic Acids Res*, 28(14):e71.
- Steinberg, G., K. Stromborg, L. Thomas, D. Barker, C. Zhao.** 2004. Strategies for covalent attachment of DNA to beads. *Biopolymers*, 73(5):597-605.
- Walsh, M.K., X. Wang, B.C. Weimer.** 2001. Optimizing the immobilization of single-stranded DNA onto glass beads. *J Biochem Biophys Methods*, 47(3):221-231.
- Weetall, H.H.** 1993. Preparation of immobilized proteins covalently coupled through silane coupling agents to inorganic supports. *Applied Biochem Biotechnol*, 41(3):157-188.

STORAGE AND STABILITY

As a general note on stability of functionalized silica, the surface is stabilized in aqueous systems by coating proteins or other large molecules that are likely to have multi-point attachment. Surface groups will be lost if the uncoated NH₂- or COOH-silica beads are stored as an aqueous suspension, or if small molecules (that have only single point attachment, e.g. peptides, oligos or small molecule dyes) are coupled and stored in aqueous buffers. These are typically stored in a solvent, e.g. acetone, ethanol, etc. Acid-washed or functionalized silica may be stored dry at room temperature or in solvent (e.g. EtOH) to preserve surface groups.

Store suspended (plain and coated) silica particles at 4°C. Freezing may result in irreversible aggregation and loss of binding activity. Coated silica microspheres should be stored in a buffer or suspending solution that is suitable for both the biomolecule and the silica matrix. Stability of coated microspheres should be determined empirically.

These products are for research use only and are not intended for use in humans or for *in vitro* diagnostic use.

ORDERING INFORMATION

Cat. #	Description	Nom. Diam.	% Solids	Size
24298	Silica Microspheres (broad distribution)	0.01µm	5	10ml
24040	Silica Microspheres	0.05µm	5	10ml
24041	Silica Microspheres	0.10µm	5	10ml
24320	Silica Microspheres	0.15µm	10	15ml
24321	Silica Microspheres	0.30µm	10	15ml
24322	Silica Microspheres	0.40µm	10	15ml
24323	Silica Microspheres	0.50µm	10	15ml
24324	Silica Microspheres	0.70µm	10	15ml
24325	Silica Microspheres	0.90µm	10	15ml
24326	Silica Microspheres	1.0µm	10	15ml
24327	Silica Microspheres	1.5µm	10	15ml
24328	Silica Microspheres	2.0µm	10	15ml
24329	Silica Microspheres	2.5µm	10	15ml
24330	Silica Microspheres	3.0µm	10	15ml
24331	Silica Microspheres	4.0µm	10	15ml
24332	Silica Microspheres	5.0µm	10	15ml
25341	Silica Microspheres – Dry	0.3µm	100	1.5g
25342	Silica Microspheres – Dry	0.5µm	100	1.5g
25343	Silica Microspheres – Dry	1.0µm	100	1.5g
25344	Silica Microspheres – Dry	1.5µm	100	1.5g
25345	Silica Microspheres – Dry	2.5µm	100	1.5g
25346	Silica Microspheres – Dry	3.0µm	100	1.5g
25347	Silica Microspheres – Dry	4.0µm	100	1.5g
25348	Silica Microspheres – Dry	5.0µm	100	1.5g
25349	Silica Microspheres – Dry	6.0µm	100	1.5g
24756	Silica Amine	0.5µm	100	1g
24757	Silica Amine	1.0µm	100	1g
24758	Silica Amine	5.0µm	100	1g
24753	Silica Carboxyl	0.5µm	100	1g
24754	Silica Carboxyl	1.0µm	100	1g
24755	Silica Carboxyl	5.0µm	100	1g
24759	Silica Streptavidin	0.5µm	1	2ml
24760	Silica Streptavidin	1.0µm	1	2ml
24761	Silica Streptavidin	5.0µm	1	2ml

TO ORDER

In The U.S. Call: 1(800) 523-2575 • (215) 343-6484
In The U.S. Fax: 1(800) 343-3291 • (215) 343-0214
In Germany Call: +(49) 6221-765767
In Germany Fax: +(49) 6221-764620
In Asia Call: (886) 2 8712 0600
In Asia Fax: (886) 2 8712 2677

Order online anytime at www.polysciences.com

Should any of our materials fail to perform to our specifications, we will be pleased to provide replacements or return the purchase price. We solicit your inquiries concerning all needs for life sciences work. The information given in this bulletin is to the best of our knowledge accurate, but no warranty is expressed or implied. It is the user's responsibility to determine the suitability for their own use of the products described herein, and since conditions of use are beyond our control, we disclaim all liability with respect to the use of any material supplied by us. Nothing contained herein shall be construed as a recommendation to use any product or to practice any process in violation of any law or any government regulation.